

Technical Data Sheet



Product name: AquaSolve™ - PVA

Date of issue: 29 October 2015

Version: v2

AquaSolve™ PVA is an “easy to use” high-end PVA (PolyVinyl Alcohol) type of 3D printer filament. AquaSolve™ PVA is a rapidly cold water soluble PolyVinyl Alcohol type of filament, which bonds extremely well to (thermo)plastics and because of its process stability is “easy to print” at relatively low temperatures.

AquaSolve™ PVA has a limited smell during printing and is non-toxic and biodegradable once dissolved in water.

Properties	Typical value	Test Method	Test condition
Physical			
Specific gravity	1.23 g/cc	ASTM D1505	-
Melt flow rate	14-20 g/10min	-	190° C/21.6Kg
Water absorption	-	-	-
Moisture absorption	-	-	-
Mechanical			
Impact strength	1.6 KJ/m ²	ISO 179	Charpy Notched @23° C (73° F)
Tensile strength	78 Mpa	ISO 527	Stress @ Yield 23° C
Tensile modulus	3860 Mpa	ISO 527	-
Elongation at break	9.90%	ISO 527	Nominal Strain at Break, 23° C
Flexural strength	-	-	-
Flexural modulus	-	-	-
Hardness	-	-	-
Thermal			
Print temperature	± 180 - 205° C	-	-
Melting temperature	± 163	-	-
Viscat softening temp.	± 60.2° C	ISO 306	VST/A/50 (50° C/h, 10N)
Optical			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance	Diameter	Tolerance	Roundness
HS Code	1.75mm	± 0.05mm	≥ 95%
REACH compliant	2.85mm	± 0.10mm	≥ 95%
RoHS certified			
FDA compliant			

Formfutura VOF	CoC: 55502105	Tel: +31 (0)85 002 0881
Groenestraat 215	VAT: NL851741083B01	Email: info@formfutura.com
6531 HH Nijmegen	EORI: NL851741083	Website: www.formfutura.com
The Netherlands		

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.